

OTTOSEAL®**S 50****Technical Datasheet****Characteristics:**

- 1-component acetate-curing silicone sealant
- Vulcanizes to a crystal-clear sealant
- Excellent weathering, ageing and UV-resistance

Fields of application:

- Bonding and sealing glass, plastics, aluminium, e. g. for glass ornaments, bonding of lattices, glass display construction, cabinets and shop windows construction
- Small area bonding

Important information:

Before applying the adhesive / sealant the user has to ensure that the materials in the area of contact (solid, liquid and gaseous) are compatible with the adhesive / sealant and do not damage or alter (e. g. discolour) them. As for the materials that will be used at a later stage in the surrounding area of the adhesive / sealant the user has to clarify beforehand that the substances of content or evaporations do not lead to an impairment or alteration (e. g. discolouration) of the adhesive / sealant. In case of doubt the user should consult the respective manufacturer of the material.

Sensitive to smoothing agents. Milky cloudiness can easily develop. If possible do not re-smoothen or use very heavily diluted soft soap solution only.

While curing small amounts of acetic acid are released.

Ensure good ventilation during application and curing.

After curing the product is completely odourless, physiologically harmless and unmodified.

The required vulcanization time prolongs with increasing thickness of the silicone layer. One-component silicones must not be used for full-surface bonding applications except special xzy are provided. If one-component silicones are to be used for thickness layers of more than 15 mm please contact our technical department beforehand.

Avoid contact with materials which contain bitumen and which release solvents, e. g. butyl, EPDM, neoprene, insulating- and bituminous paint.

Not suitable for laminated safety glass

Technical properties:

Skin-forming time at 23 °C / 50 % RAH	approx. 15 minutes
Curing in 24 hours at 23 °C / 50 % RAH	approx. 2 mm
Viscosity (23 °C)	pasty, stable
Density at 23 °C	approx. 1,0 g/cm ³
Shore-A-hardness (DIN 53 505)	approx. 16
Permissible movement capability	25 %
Stress expansion modulus at 100 % (DIN 53 504, S3A)	approx. 0,5 N/mm ²
Breaking expansion (DIN 53 504, S3A)	approx. 600 %
Tensile strength (DIN 53 504, S3A)	approx. 1,6 N/mm ²
Temperature resistance	-50 °C up to +150 °C
Shelf life at 23 °C / 50 % RAH for cartridge / foil bag	12 months

These data are not suitable for the issuing specifications. Please contact OTTO - CHEMIE before issuing specifications.

Pretreatment:

The adherent surfaces have to be clean, free from fat, dry and sustainable.



INDUSTRIEVERBAND
DICHTSTOFFE E.V.
(IVD)



INDUSTRIEVERBAND
KLEBSTOFFE E.V.
(IVK)



Sealants • Adhesives

All adherent surfaces must be clean and any contaminant such as release agents, preserving agents, grease, oil, dust, water, old adhesives or sealants and other substances which could affect adhesion, should be removed. Cleaning of non-porous substrates: Apply OTTO Cleaner T (airing time approx. 1 minute) using a clean, lint-free cotton cloth. Cleaning porous substrates: Clean surfaces with steel-wire brush e. g. or a grinding disk to remove loose particles.

Primer Table:

The demands on elastic sealings and bondings depend on the respective exterior influences. Extreme fluctuations in temperature, tensile or shear forces, repeated contact with water etc. demand high requirements of a bonding. In such cases it is advisable to apply primer according to the recommendations of our technical department (e. g. +/OTTO Primer 1216) in order to achieve a resilient bonding.

Aluminium	+
Aluminium anodized	+ / 1101
Aluminium powder-coated	1101 / T
Aluminium powder-coated (contains teflon)	T
Concrete	1105
Stainless steel	+ / 1101
Fibre cement	1105
Glass	+
Ceramic, glazed	+
Ceramics, unglazed	+
Polyester	+
PVC unplasticized	1227

+ = good adherence without primer

- = not suitable

T= Test/pilot test advised

Application information:

Ensure good adhesion by pressing and smoothing the sealant to the joint flanks. Curing time depends on the thickness of the sealant layer amongst others, ambient temperature and atmospheric humidity. Not suitable for: - joints, which are walked or driven over, - joints, which are in direct contact with food, - structural glazing – under water area – aquaria bonding – non ferrous metals, non-corrosion-resistant metals

Because of the variety of possible influences while processing and applying customer tests are required.

Please observe the recommended shelf life which is printed on the packaging.

We recommend to store our products in unopened original packagings dry (< 60 % RAH) at temperatures of +15 °C up to +25 °C. If the products are stored and / or transported at higher temperatures / air humidity for longer periods (some weeks), a diminution of durability or a change of material characteristics may arise.

Packaging:

Please see the packagings available from stock in our current General Catalogue for Building Products.

Trading unit/Container	Packaging unit	Pieces per pallet
310 ml cartridge	20	1200

Colours:

C30 crystal clear

Safety precautions:

Please observe the material safety data sheet.

Disposal:

Information about disposal: Please refer to the material safety data sheet.

Warranty information:

All information in this publication is based on our current technical knowledge and experiences. However, since conditions and methods of use and application of our products are beyond our control, we suggest you to test the product before final use. Information given in this technical data sheet and explanations of OTTO - CHEMIE in connection with this technical data sheet (e. g. service description,

reference to DIN regulations, etc.) is not to be seen as a warranty. Warranties require a separate written declaration of OTTO – CHEMIE to prove their validity. The characteristics stated in this data sheet define the characteristics of the article broadly and conclusively. Suggestions of use are not to be taken as confirmation of the appropriateness for the recommended intended use. We reserve the right to alter the product adjusting it according to technical progress and new developments. We are at your disposal both for inquiries as well as specific application problems. If a governmental approval or clearance is necessary for the application of our products, the user is responsible for the obtainment of such. Our recommendations do not excuse the user from the obligation to take into consideration the possibility of infringement of third parties' rights and - if necessary – resolving it. For the rest our general terms and conditions apply, in particular regarding a possible liability for defects. If you happen to not have our general terms and conditions at hand, we will gladly send them to you upon request. You can also find them on our homepage: http://www.otto-chemie.de/englisch/unternehmen/agb/AGB-Englisch_04-05.pdf

